


TECHNICAL DATA SHEET

K12 GLOSS

K12 GLOSS is a gloss bioriented polypropylene film with both sides corona treated.

This film is suitable to come into contact with food and complies with EN-71 (declarations on request).



TYPICAL TECHNICAL FEATURES ⁽¹⁾

PHYSICAL PROPERTIES		METHOD	UNIT	VALUE	
				code 000/50	code 000/53
Thickness		Internal	µm	12 ± 0,6	12 ± 0,72
Grammage		Internal	g/m ²	10,92 ± 0,55	10,92 ± 0,66
COF	dynamic	ASTM D1894	-	≤ 0,40	≤ 0,35
Surface tension	corona	ASTM D2578	dyne/cm	≥ 38	≥ 38

MECHANICAL PROPERTIES		METHOD	UNIT	VALUE	
				code 000/50	code 000/53
Tensile strength at break	MD	ASTM D882	MPa	≥ 130	140 - 180
	TD			≥ 240	290 - 340
Elongation at break	MD	ASTM D882	%	≤ 180	140 - 180
	TD			≤ 65	40 - 65

THERMAL PROPERTIES		METHOD	UNIT	VALUE	
				code 000/50	code 000/53
Thermal shrinkage (120°C/5min)	MD	Internal	%	≤ 6,0	4,0 ± 1,0
	TD			≤ 2,5	1,5 ± 1,0

OPTICAL PROPERTIES		METHOD	UNIT	VALUE	
				code 000/50	code 000/53
Gloss	45°	ASTM D2457	GU	≥ 88	92 ± 3
Haze		ASTM D1003	%	≤ 2,5	1,5 ± 1

⁽¹⁾ The information and data contained herein are to be used only as a guideline; therefore, ULTRALEN FILM GmbH doesn't offer any guarantee on their absolute truthfulness and doesn't accept any liability arising out of their use.

STORAGE

Store the material in a dry location (preferably with RH ≤ 50%) at a constant temperature between 10°C and 30°C. Do not leave it exposed to direct sunlight or atmospheric agents.
Partially used reels have to be repacked as originally supplied.

WARRANTY

Material processability is guaranteed up to 6 months since shipment date, as long as it is stored correctly.
It is recommended to condition the material at room temperature at least 24 hours before its use.

DISCLAIMERS

ULTRALEN FILM GmbH gives no warranty, expressed or implied, as to the suitability of the material for a specific application or characteristic use. An industrial homologation test of the material in actual conditions of purpose is always needed in order to verify its suitability for the specific application or characteristic use.

Before using the material, it is advisable to check the compatibility of the inks and adhesives to be purposed with the type and level of its treatment.

ULTRALEN FILM GmbH

LUSTGARTENSTRASSE, 6 - 79576 WEIL AM RHEIN - DEUTSCHLAND

USt.ID: DE229822516

Tel.: (0049) 76214223880 Fax: (0049) 76214223839

e-mail: info@ultralen.com web: www.ultralen.com