

TECHNICAL DATA SHEET

PETG J20 Shrink

PETG J20 Shrink is a rigid PETG shrink film, oriented in transverse direction, with double printable side. Recommended for using in steam shrink tunnels, for shrink sleeve label application. Widely used for normal bottle sleeves.

TYPICAL TECHNICAL FEATURES ⁽¹⁾

PHYSICAL PROPERTIES		METHOD	UNIT	VALUE	
				925/80 40µm	926/80 45µm
Thickness		ASTM D374	µm	40 ± 2,0	45 ± 2,25
Grammage		Internal	g/m ²	52,91 ± 2,64	59,52 ± 2,97
COF (film/film)	static	ASTM D1894	-	≤ 0,60	
	dynamic		-	≤ 0,55	
Surface tension		ASTM D2578	dyne/cm	≥ 38	


MECHANICAL PROPERTIES		METHOD	UNIT	VALUE	
				925/80 40µm	926/80 45µm
Tensile strength at break	MD	ASTM D882	MPa	≥ 45	
	TD			≥ 180	
Elongation at break	MD	ASTM D882	%	≥ 300	
	TD			≥ 25	

THERMAL PROPERTIES		METHOD	UNIT	VALUE	
				925/80 40µm	926/80 45µm
Thermal shrinkage (85°C/10s/water)	MD	ASTM D1204	%	≤ 5	
	TD			≥ 70	

OPTICAL PROPERTIES		METHOD	UNIT	VALUE	
				925/80 40µm	926/80 45µm
Haze		ASTM D1003	%	≤ 7,0	
Gloss	45°	ASTM D2457	GU	≥ 100	

⁽¹⁾ The information and data contained herein are to be used only as a guideline; therefore, ULTRALEN FILM GmbH doesn't offer any guarantee on their absolute truthfulness and doesn't accept any liability arising out of their use.

SHRINKAGE CURVE



Remark:

- ☆ Data and curves are only for reference, not as acceptance criteria.
- ☆ Test condition: 10-s hot water bath contraction.

STORAGE

Store the material in a dry location (preferably with $\cong 55$ -60%) at a constant temperature between 10°C and 30°C. Do not leave it exposed to direct sunlight or atmospheric agents. Partially used reels have to be repacked as originally supplied.

WARRANTY

Material processability is guaranteed up to 6 months since shipment date, as long as it is stored correctly. It is recommended to condition the material at room temperature at least 24 hours before its use.

DISCLAIMERS

ULTRALEN FILM GmbH gives no warranty, expressed or implied, as to the suitability of the material for a specific application or characteristic use. An industrial homologation test of the material in actual conditions of purpose is always needed in order to verify its suitability for the specific application or characteristic use. Before using the material, it is advisable to check the compatibility of the inks and adhesives to be purposed with the type and level of its treatment.

ULTRALEN FILM GmbH

LUSTGARTENSTRASSE 6 - 79576 WEIL AM RHEIN - DEUTSCHLAND

USt.ID: 229822516

Tel.: (0049) 76214223880 Fax: (0049) 76214223839

e-mail: info@ultralen.com web: www.ultralen.com